

Synergistic stabiliser mixture

Patent Number: EP0728806

Publication date: 1996-08-28

Inventor(s): GUGUMUS FRANCOIS (CH)

Applicant(s):: CIBA GEIGY AG (CH)

Requested

Patent: ☐ EP0728806, B1

Application

Number: EP19960810069 19960202

Priority Number

(s): EP19950810091 19950210

IPC Classification: C08K5/54 ; C08K5/3492 ; C08K5/3435 ; C08K5/353 ; C08L83/08

EC Classification: C08K5/3435, C08K5/3492, C08K5/3492, C08K5/3492F, C08K5/353, C08L83/08, C08K5/544B, C08K5/544B

Equivalents: BR9600376, CA2169124, CN1136048, DE59600119D, ES2115421T, ☐ JP8245834, SK17796, TW401437, ZA9601053**Abstract**

A stabiliser mixt. comprises a polyalkylpiperidine of formula (I) together with a further polyalkylpiperidine (a), (b), (c), (d), (e) or (f), where (a) is of formula (II), (b) is a reaction prod. of (i) a cyanuric chloride/polyamine of formula $H_2N(CH_2)n_3'NH(CH_2)n_3''NH(CH_2)n_3'''SB>''NH_2$ (IIIA) reaction prod. and (ii) a cpd. of formula (IIIB), (c) is of formula (IV), (d) is e.g. of formula (VA), (e) is of formula (V), and (f) is of formula (VII). $R_1 = 1-10C$ alkyl, 5-12C cycloalkyl (opt. substd. by 1-4C alkyl) or phenyl (opt. substd. by 1-10C alkyl), $R_2 = 3-10C$ alkylene, $R_3 = H$, 1-8C alkyl, O, $-CH_2CN$, 3-6C alkenyl, 7-9C phenylalkyl (opt. ring-substd. by 1-4C alkyl) or 1-8C acyl, n_1 , n_6 and $n_7 = 1-50$, R_4 and $R_6-R_8 = H$, 1-12C alkyl, 5-12C cycloalkyl (opt. substd. by 1-4C alkyl), phenyl (opt. substd. by OH and/or 1-10C alkyl), 7-9C phenylalkyl (opt. ring-substd. by OH and/or 1-10C alkyl) or $R_9-N-2,2,6,6$ -tetra-Me-piperidin-4-yl, at least one of R_4 and R_6-R_8 being this last gp., $R_5 = 2-18C$ alkylene, 5-7C cycloalkylene, 1-4C alkylenedi(5-7C cycloalkylene) or R_4-R_6 together with N form a 5-10 membered heterocycle, R_7 and $R_8 = 5-10$ membered heterocycle together with N, $R_9 =$ as for R_3 , n_2 , n_4 , n_5 and $n_5' = 2-50$, n_3' , n_3'' and $n_3''' = 2-12$, $R_{10} = H$, 1-12C alkyl, 5-12C cycloalkyl phenyl or 7-9C phenylalkyl, $R_{11} =$ as for R_3 , $R_{12} = H$ or Me, $R_{13} =$ direct bond or 1-10C alkylene, R_{14} and $R_{18} =$ direct bond or $-N(X_1).CO.X_2.CO.N(X_3)-$, X_1 and $X_3 =$ as for R_{10} but with 1-8C rather than 1-12C alkyl or $R_9-N-2,2,6$ -tetra-Me-piperidin-4-yl, $X_2 =$ direct bond or 1-4C alkylene, $R_{15} =$ as for R_3 , $R_{19} = H$, 1-30C alkyl, 5-12C cycloalkyl, 7-9C phenylalkyl, phenyl or $R_9-N-2,2,6,6$ -tetra-Me-piperidin-4-yl, $R_{22}-R_{26} =$ as for R_{13} and $R_{27} =$ as for R_3 .

Data supplied from the esp@cenet database - I2



Ottawa Hull K1A 0C9

(21) (A1) 2,169,124

(22) 1996/02/08

(43) 1996/08/11

(51) Int.Cl. ⁶ C08K 5/54; C08K 5/34; C08K 5/00; C08L 83/08; C08L
79/04; C08L 73/00; C09K 15/04

(19) (CA) **APPLICATION FOR CANADIAN PATENT** (12)

(54) Synergistic Stabilizer Mixture

(72) Gugumus, François - Switzerland ;

(71) CIBA-GEIGY AG - Switzerland ;

(30) (EP) 95810091.9 1995/02/10

(57) 14 Claims

Notice: This application is as filed and may therefore contain an
incomplete specification.




Synergistic stabilizer mixture

The present invention relates to a stabilizer system comprising two specific high-molecular-weight polyalkylpiperidine derivatives, to the use of this stabilizer system for stabilizing organic material, and to the organic material protected against thermal, oxidative or light-induced degradation by means of the stabilizer system mentioned.

US-A-4 692 486, US-A-4 863 981, US-A-4 957 953, WO-A-92/12 201, EP-A-449 685, EP-A-632 092, GB-A-2 267 499 and Research Disclosure 34549 (January 1993) describe stabilizer mixtures comprising two polyalkylpiperidine derivatives.

The present invention relates to a stabilizer mixture comprising a component a) and a component b), c), d), e), f) or g), where

component a) is at least one compound of the formula I



in which R_1 is C_1 - C_{10} alkyl, C_5 - C_{12} cycloalkyl, C_1 - C_4 alkyl-substituted C_5 - C_{12} cycloalkyl, phenyl or C_1 - C_{10} alkyl-substituted phenyl,


R_2 is C_3 - C_{10} alkylene,

R_3 is hydrogen, C_1 - C_8 alkyl, O , $-CH_2CN$, C_3 - C_6 alkenyl, C_7 - C_9 phenylalkyl,

C_7 - C_9 phenylalkyl which is substituted on the phenyl radical by C_1 - C_4 alkyl; or C_1 - C_8 acyl and,

n_1 is a number from 1 to 50;

component b) is at least one compound of the formula (II)



in which R_4 , R_6 , R_7 and R_8 , independently of one another, are hydrogen, C_1 - C_{12} alkyl, C_5 - C_{12} cycloalkyl, C_1 - C_4 -alkyl-substituted C_5 - C_{12} cycloalkyl, phenyl, phenyl which is substituted by -OH and/or C_1 - C_{10} alkyl; C_7 - C_9 phenylalkyl, C_7 - C_9 phenylalkyl which is substituted on the phenyl radical by -OH and/or C_1 - C_{10} alkyl; or a group of the formula III



R_5 is C_2 - C_{18} alkylene, C_5 - C_7 cycloalkylene or C_1 - C_4 alkylenedi(C_5 - C_7 cycloalkylene), or the radicals R_4 , R_5 and R_6 , together with the nitrogen atoms to which they are bonded, perform a 5- to 10-membered heterocyclic ring, or


R_7 and R_8 , together with the nitrogen atom to which they are bonded, form a 5- to 10-membered heterocyclic ring,

R_9 is as defined for R_3 ,

n_2 is a number from 2 to 50, and

at least one of the radicals R_4 , R_6 , R_7 and R_8 is a group of the formula (III);


component c) is a product obtainable by reacting a product, obtained by reaction of a polyamine of the formula IVa with cyanuric chloride, with a compound of the formula IVb






in which n_3' , n_3'' and n_3''' , independently of one another are a number from 2 to 12,
 R_{10} is hydrogen, C_1 - C_{12} alkyl, C_5 - C_{12} cycloalkyl, phenyl or C_7 - C_9 phenylalkyl, and
 R_{11} is as defined for R_3 ;


component d) is at least one compound of the formula (V)



in which R_{12} is hydrogen or methyl,
 R_{13} is a direct bond or C_1 - C_{10} alkylene and
 n_4 is a number from 2 to 50;


component e) is at least one compound of the formulae (VIa) and (VIb)





in which n_5 and n_5^* independently of one another are a number from 2 to 50;

component f) is at least one compound of the formula (VII)



in which R_{14} and R_{18} , independently of one another, are a direct bond or an $-N(X_1)-CO-X_2-CO-N(X_3)-$ group, where X_1 and X_3 , independently of one another, are hydrogen, C_1-C_8 alkyl, C_5-C_{12} cycloalkyl, phenyl, C_7-C_9 phenylalkyl or a group of the formula III,

X_2 is a direct bond or C_1-C_4 alkylene,


R_{15} is as defined for R_3 ,

R_{16} , R_{17} , R_{20} and R_{21} , independently of one another, are hydrogen, C_1-C_{30} alkyl, C_5-C_{12} cycloalkyl or phenyl,

R_{19} is hydrogen, C_1-C_{30} alkyl, C_5-C_{12} cycloalkyl, C_7-C_9 phenylalkyl, phenyl or a group of the formula III, and

n_6 is a number from 1 to 50;

component g) is at least one compound of the formula (VIII)



in which R_{22} , R_{23} , R_{24} , R_{25} and R_{26} , independently of one another, are a direct bond or C_1 - C_{10} alkylene,

R_{27} is as defined for R_3 , and

n_7 is a number from 1 to 50.

Examples of alkyl having up to 30 carbon atoms are methyl, ethyl, propyl, isopropyl, n-butyl, sec-butyl, isobutyl, tert-butyl, 2-ethylbutyl, n-pentyl, isopentyl, 1-methylpentyl, 1,3-dimethylbutyl, n-hexyl, 1-methylhexyl, n-heptyl, isoheptyl, 1,1,3,3-tetramethylbutyl, 1-methylheptyl, 3-methylheptyl, n-octyl, 2-ethylhexyl, 1,1,3-trimethylhexyl, 1,1,3,3-tetramethylpentyl, nonyl, decyl, undecyl, 1-methylundecyl, dodecyl, 1,1,3,3,5,5-hexamethylhexyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, eicosyl, docosyl and triacontyl. One of the preferred meanings of R_3 , R_9 , R_{11} , R_{15} , R_{17} , R_{21} and R_{27} is C_1 - C_4 alkyl, in particular methyl. One of the preferred meanings of R_{16} and R_{20} is C_1 - C_{25} alkyl, in particular C_{15} - C_{25} alkyl, for example hexadecyl and C_{18} - C_{22} alkyl. One of the preferred meanings of R_{19} is C_1 - C_{25} alkyl, in particular octadecyl.

Examples of C_5 - C_{12} cycloalkyl are cyclopentyl, cyclohexyl, cycloheptyl, cyclooctyl and cyclododecyl. C_5 - C_8 cycloalkyl, in particular cyclohexyl, is preferred.

C_1 - C_4 Alkyl-substituted C_5 - C_{12} cycloalkyl is, for example, methylcyclohexyl or dimethylcyclohexyl.

Phenyl which is substituted by -OH and/or C_1 - C_{10} alkyl is, for example, methylphenyl,

dimethylphenyl, trimethylphenyl, tert-butylphenyl or 3,5-di-tert-butyl-4-hydroxyphenyl.

Examples of C₇-C₉phenylalkyl are benzyl and phenylethyl.

C₇-C₉phenylalkyl which is substituted by -OH and/or alkyl with up to 10 carbon atoms on the phenyl radical is, for example, methylbenzyl, dimethylbenzyl, trimethylbenzyl, tert-butylbenzyl, or 3,5-di-tert-butyl-4-hydroxyphenyl.

Examples of C₃-C₆alkenyl are allyl, 2-methallyl, butenyl, pentenyl and hexenyl. Allyl is preferred.


C₁-C₈acyl is preferably C₁-C₃alkanoyl, C₃-C₈alkenoyl or benzoyl. Examples are formyl, acetyl, propionyl, butyryl, pentanoyl, hexanoyl, octanoyl, benzoyl, acryloyl and crotonyl.

Examples of alkylene having up to 18 carbon atoms are methylene, ethylene, propylene, trimethylene, tetramethylene, pentamethylene, 2,2-dimethyltrimethylene, hexamethylene, trimethylhexamethylene, octamethylene and decamethylene. R₅ is preferably hexamethylene, R₁₃ is preferably ethylene, R₂₂ and R₂₄ are preferably methylene, R₂₅ is preferably 2,2-dimethylethylene and R₂₆ is preferably 1,1-dimethylethylene.

An example of C₅-C₇cycloalkylene is cyclohexylene.

An example of C₁-C₄alkylenedi(C₅-C₇cycloalkylene) is methylenedicyclohexylene.

If the radicals R₄, R₅ and R₆, together with the nitrogen atoms to which they are bonded, form a 5- to 10-membered heterocyclic ring, this is, for example,



A 6-membered heterocyclic ring is preferred.

If the radicals R₇ and R₈, together with the nitrogen atom to which they are bonded, form a 5- to 10-membered heterocyclic ring, this is, for example, 1-pyrrolidyl, piperidino,

morpholino, 1-piperazinyl, 4-methyl-1-piperazinyl, 1-hexahydroazepinyl, 5,5,7-trimethyl-1-homopiperazinyl or 4,5,5,7-tetramethyl-1-homopiperazinyl. Morpholino is particularly preferred.

One of the preferred meanings of R_{16} and R_{20} is phenyl.

X_2 and R_{23} are preferably a direct bond.

X_1 , X_3 , R_3 , R_9 , R_{11} , R_{15} and R_{27} are preferably hydrogen.

n_1 is preferably 1-25, in particular 2-20 or 2-10.

n_2 is preferably 2-25.

n_3' , n_3'' , n_3''' are preferably 2-4.

n_4 is preferably 2-25, in particular 2-20 or 2-10.

n_5 and n_5^* are preferably 2-25, in particular 2-20 or 2-10.

n_6 is preferably 1-25, in particular 1-20 or 1-10.

n_7 is preferably 1-25, in particular 1-20 or 1-10.

The compounds described as components a) to g) are essentially known (in some cases commercially available) and can be prepared by known processes, for example as described in US-A-5 051 458, US-A-4 086 204, US-A-4 331 586, US-A-4 477 615 and Chemical Abstracts - CAS No. 136 504-96-6, US-A-4 233 412, US-A-4 340 534, US-A-4 857 595, DD-A-262 439 (Derwent 89-122 983/17, Chemical Abstracts 111:58 964u), DE-A-4 239 437 (Derwent 94-177 274/22) and US-A-4 529 760.


Component c) can be prepared analogously to known processes, for example by reaction of a polyamine of the formula IVa with cyanuric chloride in a molar ratio of from 1:2 to 1:4 in the presence of anhydrous lithium carbonate, sodium carbonate or potassium carbonate in an organic solvent, such as 1,2-dichloroethane, toluene, xylene, benzene, dioxane or tert-amyl alcohol, at a temperature of from -20°C to +10°C, preferably from -10°C to +10°C, in particular from 0°C to +10°C, for from 2 to 8 hours, followed by reaction of the resultant product with a 2,2,6,6-tetramethyl-4-piperidylamine of the formula IVb. The molar ratio between 2,2,6,6-tetramethyl-4-piperidylamine and polyamine of the formula IVa is, for example, from 4:1 to 8:1. The amount of 2,2,6,6-tetramethyl-4-piperidylamine can be added in one portion or in more than one portion at intervals of a few hours.



The polyamine of the formula IVa:cyanuric chloride:2,2,6,6-tetramethyl-4-piperidylamine of the formula IVb ratio is preferably from 1:3:5 to 1:3:6.

The following example indicates one way of preparing the preferred component c).

Example: 23.6 g (0.128 mol) of cyanuric chloride, 7.43 g (0.0426 mol) of N,N'-bis[3-aminopropyl]ethylenediamine and 18 g (0.13 mol) of anhydrous potassium carbonate are reacted at 5°C for 3 hours with stirring in 250 ml of 1,2-dichloroethane. The mixture is warmed at room temperature for a further 4 hours. 27.2 g (0.128 mol) of N-(2,2,6,6-tetramethyl-4-piperidyl)butylamine are added, and the resultant mixture is warmed at 60°C for 2 hours. A further 18 g (0.13 mol) of anhydrous potassium carbonate are added, and the mixture is warmed at 60°C for a further 6 hours. The solvent is removed by distillation under a slight vacuum (200 mbar) and replaced by xylene. 18.2 g (0.085 mol) of N-(2,2,6,6-tetramethyl-4-piperidyl)butylamine and 5.2 g (0.13 mol) of ground sodium hydroxide are added, the mixture is refluxed for 2 hours and, after a further 12 hours, the water formed during the reaction is removed by azeotropic distillation. The mixture is filtered. The solution is washed with water and dried over Na₂SO₄. The solvent is evaporated, and the residue is dried at 120-130°C in vacuo (0.1 mbar). Component c) is obtained as a colourless resin.


In general, component c) can be represented for example by a compound of the formula IV-1, IV-2 or IV-3. It can also be in the form of a mixture of these three compounds.






A preferred meaning of the formula IV-1 is


2169124



A preferred meaning of the formula IV-2 is



A preferred meaning of the formula IV-3 is



In the above formulae IV-1 to IV-3, n_3 is preferably 1 to 20.


Component a) is preferably [®]UVASIL 299 or [®]UVASIL 125, component b) is preferably [®]CHIMASSORB 944, [®]CYASORB UV 3346 or [®]DASTAB 1082, component c) is preferably [®]UVASORB HA 88, component d) is preferably [®]TINUVIN 622, component e) is preferably [®]HOSTAVIN N 30, component f) is preferably [®]UVINUL 5050 H, [®]LICHTSCHUTZSTOFF UV 31 or [®]LUCHEM B 18, and component g) is preferably [®]MARK LA 63 or [®]MARK LA 68.

The compounds of the formulae VIa and VIb can be formed together as a mixture and also employed as such as component e) in the novel stabilizer system. The VIa:VIb ratio is, for example, from 20:1 to 1:20 or from 1:10 to 10:1.

The meanings of the terminal groups which saturate the free valences in the compounds of the formulae I, II, IV-1, IV-2, IV-3, V, VIa, VIb, VII and VIII depend on the processes used for their preparation. The terminal groups can also be modified after the preparation of the compounds.


In the compounds of the formula I, the terminal group bonded to the silicon atom can be, for example, $(R_1)_3Si-O-$, and the terminal group bonded to the oxygen can be, for example, $-Si(R_1)_3$.

If the compounds of the formula II are prepared by reacting a compound of the formula



$$\begin{array}{c} \text{H}-\text{N}-\text{R}_5-\text{N}-\text{H}, \\ | \qquad \qquad | \\ \text{R}_4 \qquad \qquad \text{R}_6 \end{array}$$
c1nc()nc(NR7R8)c1
$$\begin{array}{c} \text{---N---R}_5\text{---N---H} \\ | \qquad \qquad | \\ \text{R}_4 \qquad \qquad \text{R}_6 \end{array}$$

If X is halogen, it is advantageous to replace this, for example, by -OH or an amino group when the reaction is complete. Examples of amino groups which may be mentioned are pyrrolidin-1-yl, morpholino, -NH₂, -N(C₁-C₈alkyl)₂ and -NR(C₁-C₈alkyl), in which R is hydrogen or a group of the formula III.

In the compounds of the formulae IV-1, IV-2 and IV-3, the terminal group bonded to the triazine radical is, for example, Cl or a




group, and the terminal group bonded to the amino radical is, for example, hydrogen or a




group.

If the compounds of the formula V are prepared, for example, by reacting a compound of the formula




in which R₁₂ is hydrogen or methyl, with a dicarboxylic acid diester of the formula Y-OOC-R₁₃-COO-Y, in which Y is, for example, methyl, ethyl or propyl, and R₁₃ is as

defined above, the terminal group bonded to the 2,2,6,6-tetramethyl-4-oxypiperidin-1-yl radical is hydrogen or $-\text{CO}-\text{R}_{13}-\text{COO}-\text{Y}$, and the terminal group bonded to the diacyl radical is $-\text{O}-\text{Y}$ or




In the compounds of the formula VIa, the terminal group bonded to the nitrogen can be, for example, hydrogen and the terminal group bonded to the 2-hydroxypropylene radical can be, for example, a




group.

In the compounds of the formula VIb, the terminal group bonded to the dimethylene radical can be, for example, $-\text{OH}$, and the terminal group bonded to the oxygen can be, for example, hydrogen. The terminal groups can also be polyether radicals.


In the compounds of the formula VII, the terminal group bonded to the 2,5-dioxypyrrolidine ring is, for example, hydrogen, and the terminal group bonded to the $-\text{C}(\text{R}_{20})(\text{R}_{21})-$ radical is, for example,



In the compounds of the formula VIII, the terminal group bonded to the carbonyl radical is, for example,



and the terminal group bonded to the oxygen radical is, for example,



Preference is given to stabilizer mixtures in which R_3 , R_9 , R_{11} , R_{15} and R_{27} are hydrogen or methyl.

Preference is likewise given to stabilizer mixtures in which R_1 is C_1 - C_4 alkyl, C_5 - C_8 cycloalkyl or phenyl, R_2 is C_3 - C_6 alkylene, and n_1 is a number from 1 to 25;

R_4 , R_6 , R_7 and R_8 , independently of one another, are hydrogen, C_1 - C_8 alkyl, C_5 - C_8 cycloalkyl, phenyl, C_7 - C_9 phenylalkyl or a group of the formula III, or the radicals R_7 and R_8 , together with the nitrogen atom to which they are bonded, form a 6-membered heterocyclic ring,

R_5 is C_2 - C_{10} alkylene, and

n_2 is a number from 2 to 25;

n_3' , n_3'' and n_3''' , independently of one another, are a number from 2 to 4, and

R_{10} is C_1 - C_4 alkyl;

R_{12} is hydrogen,

R_{13} is ethylene, and

n_4 is a number from 2 to 25;

n_5 and n_5^* , independently of one another, are a number from 2 to 25;

R_{14} and R_{18} are a direct bond or an $-N(X_1)-CO-X_2-CO-N(X_3)-$ group,

X_1 and X_3 , independently of one another, are hydrogen or C_1 - C_4 alkyl, X_2 is a direct bond,

R_{16} and R_{20} are C_1 - C_{25} alkyl or phenyl,

R_{17} and R_{21} are hydrogen or C_1 - C_4 alkyl,

R_{19} is C_1 - C_{25} alkyl or a group of the formula III, and


n_6 is a number from 1 to 25;

R_{22} , R_{24} , R_{25} and R_{26} are C_1 - C_4 alkylene,

R_{23} is a direct bond, and




n_7 is a number from 1 to 25.

Particular preference is given to stabilizer mixtures in which component a) is at least one compound of the formula I-A




in which n_1 is a number from 1 to 20;

component b) is at least one compound of the formula (II-B-1), (II-B-2) or (II-B-3)




in which n_2 is a number from 2 to 20;


component c) is a product obtainable by reacting a product, obtained by reaction of a polyamine of the formula



with cyanuric chloride, with a compound of the formula





component d) is at least one compound of the formula (V-D)




in which n_4 is a number from 2 to 20;

n_5 and n_5^* in component e) are, independently of one another, a number from 2 to 20;


component f) is at least one compound of the formula (VII-F-1), (VII-F-2) or (VII-F-3)





in which n_6 is a number from 1 to 20;

component g) is at least one compound of the formula (VIII-G)




in which R_{27} is hydrogen or methyl, and n_7 is a number from 1 to 20.

The following stabilizer mixtures may be mentioned as examples:


1. a stabilizer mixture comprising components a) and b),
2. a stabilizer mixture comprising components a) and c),
3. a stabilizer mixture comprising components a) and d),
4. a stabilizer mixture comprising components a) and e),
5. a stabilizer mixture comprising components a) and f) and
6. a stabilizer mixture comprising components a) and g).

Particular preference is given to the following stabilizer systems:

- a) a stabilizer mixture comprising at least one compound of the formula (I-A) and at least one compound of the formula (II-B-1),
- b) a stabilizer mixture comprising at least one compound of the formula (I-A) and at least one compound of the formula (II-B-3),
- c) a stabilizer mixture comprising at least one compound of the formula (I-A) and a product obtainable by reacting a product, obtained by reaction of a polyamine of the formula



with cyanuric chloride, with a compound of the formula



- d) a stabilizer mixture comprising at least one compound of the formula (I-A) and at least one compound of the formula (V-D), and
- e) a stabilizer mixture comprising at least one compound of the formula (I-A) and at least one compound of the formulae (VIa) and (VIb).

In the abovementioned stabilizer systems, the two components are particularly preferably in a weight ratio of 1:1.

The novel stabilizer mixture is suitable for stabilizing organic materials against thermal, oxidative or light-induced degradation. Examples of such materials are the following:

1. Polymers of monoolefins and diolefins, for example polypropylene, polyisobutylene, polybut-1-ene, poly-4-methylpent-1-ene, polyisoprene or polybutadiene, as well as polymers of cycloolefins, for instance of cyclopentene or norbornene, polyethylene (which optionally can be crosslinked), for example high density polyethylene (HDPE), high density and high molecular weight polyethylene (HDPE-HMW), high density and ultrahigh molecular weight polyethylene (HDPE-UHMW), medium density polyethylene (MDPE),

low density polyethylene (LDPE), linear low density polyethylene (LLDPE), branched low density polyethylene (BLDPE).

Polyolefins, i.e. the polymers of monoolefins exemplified in the preceding paragraph, preferably polyethylene and polypropylene, can be prepared by different, and especially by the following, methods:

- a) radical polymerisation (normally under high pressure and at elevated temperature).
- b) catalytic polymerisation using a catalyst that normally contains one or more than one metal of groups IVb, Vb, VIb or VIII of the Periodic Table. These metals usually have one or more than one ligand, typically oxides, halides, alcoholates, esters, ethers, amines, alkyls, alkenyls and/or aryls that may be either π - or σ -coordinated. These metal complexes may be in the free form or fixed on substrates, typically on activated magnesium chloride, titanium(III) chloride, alumina or silicon oxide. These catalysts may be soluble or insoluble in the polymerisation medium. The catalysts can be used by themselves in the polymerisation or further activators may be used, typically metal alkyls, metal hydrides, metal alkyl halides, metal alkyl oxides or metal alkyloxanes, said metals being elements of groups Ia, IIa and/or IIIa of the Periodic Table. The activators may be modified conveniently with further ester, ether, amine or silyl ether groups. These catalyst systems are usually termed Phillips, Standard Oil Indiana, Ziegler (-Natta), TNZ (DuPont), metallocene or single site catalysts (SSC).

2. Mixtures of the polymers mentioned under 1), for example mixtures of polypropylene with polyisobutylene, polypropylene with polyethylene (for example PP/HDPE, PP/LDPE) and mixtures of different types of polyethylene (for example LDPE/HDPE).

3. Copolymers of monoolefins and diolefins with each other or with other vinyl monomers, for example ethylene/propylene copolymers, linear low density polyethylene (LLDPE) and mixtures thereof with low density polyethylene (LDPE), propylene/but-1-ene copolymers, propylene/isobutylene copolymers, ethylene/but-1-ene copolymers, ethylene/hexene copolymers, ethylene/methylpentene copolymers, ethylene/heptene copolymers, ethylene/octene copolymers, propylene/butadiene copolymers, isobutylene/isoprene copolymers, ethylene/alkyl acrylate copolymers, ethylene/alkyl methacrylate

copolymers, ethylene/vinyl acetate copolymers and their copolymers with carbon monoxide or ethylene/acrylic acid copolymers and their salts (ionomers) as well as terpolymers of ethylene with propylene and a diene such as hexadiene, dicyclopentadiene or ethylidene-norbornene; and mixtures of such copolymers with one another and with polymers mentioned in 1) above, for example polypropylene/ethylene-propylene copolymers, LDPE/ethylene-vinyl acetate copolymers (EVA), LDPE/ethylene-acrylic acid copolymers (EAA), LLDPE/EVA, LLDPE/EAA and alternating or random polyalkylene/carbon monoxide copolymers and mixtures thereof with other polymers, for example polyamides.

4. Hydrocarbon resins (for example C₅-C₉) including hydrogenated modifications thereof (e.g. tackifiers) and mixtures of polyalkylenes and starch.

5. Polystyrene, poly(p-methylstyrene), poly(α-methylstyrene).

6. Copolymers of styrene or α-methylstyrene with dienes or acrylic derivatives, for example styrene/butadiene, styrene/acrylonitrile, styrene/alkyl methacrylate, styrene/butadiene/alkyl acrylate, styrene/butadiene/alkyl methacrylate, styrene/maleic anhydride, styrene/acrylonitrile/methyl acrylate; mixtures of high impact strength of styrene copolymers and another polymer, for example a polyacrylate, a diene polymer or an ethylene/propylene/diene terpolymer; and block copolymers of styrene such as styrene/butadiene/styrene, styrene/isoprene/styrene, styrene/ethylene/butylene/styrene or styrene/ethylene/propylene/styrene.

7. Graft copolymers of styrene or α-methylstyrene, for example styrene on polybutadiene, styrene on polybutadiene-styrene or polybutadiene-acrylonitrile copolymers; styrene and acrylonitrile (or methacrylonitrile) on polybutadiene; styrene, acrylonitrile and methyl methacrylate on polybutadiene; styrene and maleic anhydride on polybutadiene; styrene, acrylonitrile and maleic anhydride or maleimide on polybutadiene; styrene and maleimide on polybutadiene; styrene and alkyl acrylates or methacrylates on polybutadiene; styrene and acrylonitrile on ethylene/propylene/diene terpolymers; styrene and acrylonitrile on polyalkyl acrylates or polyalkyl methacrylates, styrene and acrylonitrile on acrylate/butadiene copolymers, as well as mixtures thereof with the copolymers listed under 6), for example the copolymer mixtures known as ABS, MBS, ASA or AES polymers.

8. Halogen-containing polymers such as polychloroprene, chlorinated rubbers, chlorinated and brominated copolymer of isobutylene-isoprene (halobutyl rubber), chlorinated or sulfochlorinated polyethylene, copolymers of ethylene and chlorinated ethylene, epichlo-

rohydrin homo- and copolymers, especially polymers of halogen-containing vinyl compounds, for example polyvinyl chloride, polyvinylidene chloride, polyvinyl fluoride, polyvinylidene fluoride, as well as copolymers thereof such as vinyl chloride/vinylidene chloride, vinyl chloride/vinyl acetate or vinylidene chloride/vinyl acetate copolymers.

9. Polymers derived from α,β -unsaturated acids and derivatives thereof such as polyacrylates and polymethacrylates; polymethyl methacrylates, polyacrylamides and polyacrylonitriles, impact-modified with butyl acrylate.

10. Copolymers of the monomers mentioned under 9) with each other or with other unsaturated monomers, for example acrylonitrile/ butadiene copolymers, acrylonitrile/-alkyl acrylate copolymers, acrylonitrile/alkoxyalkyl acrylate or acrylonitrile/vinyl halide copolymers or acrylonitrile/ alkyl methacrylate/butadiene terpolymers.

11. Polymers derived from unsaturated alcohols and amines or the acyl derivatives or acetals thereof, for example polyvinyl alcohol, polyvinyl acetate, polyvinyl stearate, polyvinyl benzoate, polyvinyl maleate, polyvinyl butyral, polyallyl phthalate or polyallyl melamine; as well as their copolymers with olefins mentioned in 1) above.

12. Homopolymers and copolymers of cyclic ethers such as polyalkylene glycols, polyethylene oxide, polypropylene oxide or copolymers thereof with bisglycidyl ethers.

13. Polyacetals such as polyoxymethylene and those polyoxymethylenes which contain ethylene oxide as a comonomer; polyacetals modified with thermoplastic polyurethanes, acrylates or MBS.

14. Polyphenylene oxides and sulfides, and mixtures of polyphenylene oxides with styrene polymers or polyamides.

15. Polyurethanes derived from hydroxyl-terminated polyethers, polyesters or polybutadienes on the one hand and aliphatic or aromatic polyisocyanates on the other, as well as precursors thereof.

16. Polyamides and copolyamides derived from diamines and dicarboxylic acids and/or from aminocarboxylic acids or the corresponding lactams, for example polyamide 4, polyamide 6, polyamide 6/6, 6/10, 6/9, 6/12, 4/6, 12/12, polyamide 11, polyamide 12, aromatic polyamides starting from m-xylene diamine and adipic acid; polyamides prepared from

hexamethylenediamine and isophthalic or/and terephthalic acid and with or without an elastomer as modifier, for example poly-2,4,4-trimethylhexamethylene terephthalamide or poly-m-phenylene isophthalamide; and also block copolymers of the aforementioned polyamides with polyolefins, olefin copolymers, ionomers or chemically bonded or grafted elastomers; or with polyethers, e.g. with polyethylene glycol, polypropylene glycol or polytetramethylene glycol; as well as polyamides or copolyamides modified with EPDM or ABS; and polyamides condensed during processing (RIM polyamide systems).

17. Polyureas, polyimides, polyamide-imides, polyetherimids, polyesterimids, polyhydantoins and polybenzimidazoles.

18. Polyesters derived from dicarboxylic acids and diols and/or from hydroxycarboxylic acids or the corresponding lactones, for example polyethylene terephthalate, polybutylene terephthalate, poly-1,4-dimethylolcyclohexane terephthalate and polyhydroxybenzoates, as well as block copolyether esters derived from hydroxyl-terminated polyethers; and also polyesters modified with polycarbonates or MBS.

19. Polycarbonates and polyester carbonates.

20. Polysulfones, polyether sulfones and polyether ketones.

21. Crosslinked polymers derived from aldehydes on the one hand and phenols, ureas and melamines on the other hand, such as phenol/formaldehyde resins, urea/formaldehyde resins and melamine/formaldehyde resins.

22. Drying and non-drying alkyd resins.

23. Unsaturated polyester resins derived from copolyesters of saturated and unsaturated dicarboxylic acids with polyhydric alcohols and vinyl compounds as crosslinking agents, and also halogen-containing modifications thereof of low flammability.

24. Crosslinkable acrylic resins derived from substituted acrylates, for example epoxy acrylates, urethane acrylates or polyester acrylates.

25. Alkyd resins, polyester resins and acrylate resins crosslinked with melamine resins, urea resins, isocyanates, isocyanurates, polyisocyanates or epoxy resins.

26. Crosslinked epoxy resins derived from aliphatic, cycloaliphatic, heterocyclic or aromatic glycidyl compounds, e.g. products of diglycidyl ethers of bisphenol A and bisphenol F, which are crosslinked with customary hardeners such as anhydrides or amines, with or without accelerators.

27. Natural polymers such as cellulose, rubber, gelatin and chemically modified homologous derivatives thereof, for example cellulose acetates, cellulose propionates and cellulose butyrates, or the cellulose ethers such as methyl cellulose; as well as rosins and their derivatives.

28. Blends of the aforementioned polymers (polyblends), for example PP/EPDM, Polyamide/EPDM or ABS, PVC/EVA, PVC/ABS, PVC/MBS, PC/ABS, PBTP/ABS, PC/ASA, PC/PBT, PVC/CPE, PVC/acrylates, POM/thermoplastic PUR, PC/thermoplastic PUR, POM/acrylate, POM/MBS, PPO/HIPS, PPO/PA 6.6 and copolymers, PA/HDPE, PA/PP, PA/PPO, PBT/PC/ABS or PBT/PET/PC.

29. Naturally occurring and synthetic organic materials which are pure monomeric compounds or mixtures of such compounds, for example mineral oils, animal and vegetable fats, oil and waxes, or oils, fats and waxes based on synthetic esters (e.g. phthalates, adipates, phosphates or trimellitates) and also mixtures of synthetic esters with mineral oils in any weight ratios, typically those used as spinning compositions, as well as aqueous emulsions of such materials.

30. Aqueous emulsions of natural or synthetic rubber, e.g. natural latex or latices of carboxylated styrene/butadiene copolymers.

The invention therefore furthermore relates to a composition comprising an organic material which is sensitive to oxidative, thermal or light-induced degradation and a novel stabilizer mixture.

The organic material is preferably a synthetic polymer, in particular from one of the above groups. Polyolefins are preferred, and polyethylene, polypropylene and copolymers thereof are particularly preferred.

The components of the novel stabilizer system can be added to the material to be stabilized either individually or mixed with one another. The components can be employed, independently of one another, in amounts of from 0.01 to 4.99 %, with the

proviso that the total amount of component a) and component b), c), d), e), f) or g) is from 0.02 to 5 %, based on the total weight of the material to be stabilized.

The total amount of component a) and component b), c), d), e), f) or g) is preferably from 0.05 to 3 %, in particular from 0.05 to 2 %, or from 0.05 to 1 %, based on the total weight of the material to be stabilized.

The weight ratio between component a) and component b), c), d), e), f) or g) is preferably from 20:1 to 1:20, in particular from 10:1 to 1:10, for example from 5:1 to 1:5.

The novel stabilizer mixture or the individual components thereof can be incorporated into the organic material by known methods, for example before or during shaping or by applying the dissolved or dispersed compounds to the organic material, if necessary with subsequent evaporation of the solvent. The individual components of the novel stabilizer mixture can be added to the materials to be stabilized in the form of a powder, granules or a masterbatch, which contains these components in, for example, a concentration of from 2.5 to 25 % by weight.

If desired, the components of the novel stabilizer system can be melt blended with each other before incorporation in the organic material.

The novel stabilizer system or its components can be added before or during the polymerization or before the crosslinking.

The materials stabilized in this way can be used in a wide variety of forms, for example as films, fibres, tapes, moulding compositions, profiles or as binders for paints, adhesives or putties.

The stabilized organic materials of the invention may additionally also contain various conventional additives, for example:

1. Antioxidants

1.1. Alkylated monophenols, for example 2,6-di-tert-butyl-4-methylphenol, 2-tert-butyl-4,6-dimethylphenol, 2,6-di-tert-butyl-4-ethylphenol, 2,6-di-tert-butyl-4-n-butylphenol, 2,6-di-tert-butyl-4-isobutylphenol, 2,6-dicyclopentyl-4-methylphenol, 2-(α -methylcyclohexyl)-4,6-dimethylphenol, 2,6-dioctadecyl-4-methylphenol, 2,4,6-tricyclohexylphenol,

2,6-di-tert-butyl-4-methoxymethylphenol, nonylphenols which are linear or branched in the side chains, for example, 2,6-di-nonyl-4-methylphenol, 2,4-dimethyl-6-(1'-methylundec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methylheptadec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methyltridec-1'-yl)phenol and mixtures thereof.

1.2. Alkylthiomethylphenols, for example 2,4-dioctylthiomethyl-6-tert-butylphenol, 2,4-dioctylthiomethyl-6-methylphenol, 2,4-dioctylthiomethyl-6-ethylphenol, 2,6-di-dodecylthiomethyl-4-nonylphenol.

1.3. Hydroquinones and alkylated hydroquinones, for example 2,6-di-tert-butyl-4-methoxyphenol, 2,5-di-tert-butylhydroquinone, 2,5-di-tert-amylhydroquinone, 2,6-di-phenyl-4-octadecyloxyphenol, 2,6-di-tert-butylhydroquinone, 2,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyphenyl stearate, bis-(3,5-di-tert-butyl-4-hydroxyphenyl) adipate.

1.4. Tocopherols, for example α -tocopherol, β -tocopherol, γ -tocopherol, δ -tocopherol and mixtures thereof (Vitamin E).

1.5. Hydroxylated thiodiphenyl ethers, for example 2,2'-thiobis(6-tert-butyl-4-methylphenol), 2,2'-thiobis(4-octylphenol), 4,4'-thiobis(6-tert-butyl-3-methylphenol), 4,4'-thiobis(6-tert-butyl-2-methylphenol), 4,4'-thiobis-(3,6-di-sec-amylphenol), 4,4'-bis-(2,6-dimethyl-4-hydroxyphenyl) disulfide.

1.6. Alkylidenebisphenols, for example 2,2'-methylenebis(6-tert-butyl-4-methylphenol), 2,2'-methylenebis(6-tert-butyl-4-ethylphenol), 2,2'-methylenebis[4-methyl-6-(α -methylcyclohexyl)phenol], 2,2'-methylenebis(4-methyl-6-cyclohexylphenol), 2,2'-methylenebis(6-nonyl-4-methylphenol), 2,2'-methylenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(6-tert-butyl-4-isobutylphenol), 2,2'-methylenebis[6-(α -methylbenzyl)-4-nonylphenol], 2,2'-methylenebis[6-(α,α -dimethylbenzyl)-4-nonylphenol], 4,4'-methylenebis(2,6-di-tert-butylphenol), 4,4'-methylenebis(6-tert-butyl-2-methylphenol), 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 2,6-bis(3-tert-butyl-5-methyl-2-hydroxybenzyl)-4-methylphenol, 1,1,3-tris(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)-3-n-dodecylmercaptobutane, ethylene glycol bis[3,3-bis(3'-tert-butyl-4'-hydroxyphenyl)butyrate], bis(3-tert-butyl-4-hydroxy-5-methylphenyl)dicyclopentadiene, bis[2-(3'-tert-butyl-2'-hydroxy-5'-methylbenzyl)-6-tert-butyl-4-methylphenyl]terephthalate, 1,1-bis-(3,5-dimethyl-2-hydroxyphenyl)butane, 2,2-bis-(3,5-di-tert-butyl-4-hydroxyphenyl)propane, 2,2-bis-(5-

tert-butyl-4-hydroxy-2-methylphenyl)-4-n-dodecylmercaptobutane, 1,1,5,5-tetra-(5-tert-butyl-4-hydroxy-2-methylphenyl)pentane.

1.7. O-, N- and S-benzyl compounds, for example 3,5,3',5'-tetra-tert-butyl-4,4'-dihydroxydibenzyl ether, octadecyl-4-hydroxy-3,5-dimethylbenzylmercaptoacetate, tridecyl-4-hydroxy-3,5-di-tert-butylbenzylmercaptoacetate, tris(3,5-di-tert-butyl-4-hydroxybenzyl)-amine, bis(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)dithioterephthalate, bis(3,5-di-tert-butyl-4-hydroxybenzyl)sulfide, isooctyl-3,5-di-tert-butyl-4-hydroxybenzylmercaptoacetate.

1.8. Hydroxybenzylated malonates, for example dioctadecyl-2,2-bis-(3,5-di-tert-butyl-2-hydroxybenzyl)-malonate, di-octadecyl-2-(3-tert-butyl-4-hydroxy-5-methylbenzyl)-malonate, di-dodecylmercaptoethyl-2,2-bis-(3,5-di-tert-butyl-4-hydroxybenzyl)malonate, bis-[4-(1,1,3,3-tetramethylbutyl)phenyl]-2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate.

1.9. Aromatic hydroxybenzyl compounds, for example 1,3,5-tris-(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene, 1,4-bis(3,5-di-tert-butyl-4-hydroxybenzyl)-2,3,5,6-tetramethylbenzene, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)phenol.

1.10. Triazine Compounds, for example 2,4-bis(octylmercapto)-6-(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,3,5-triazine, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,2,3-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)isocyanurate, 1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)isocyanurate, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenylethyl)-1,3,5-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)-hexahydro-1,3,5-triazine, 1,3,5-tris(3,5-dicyclohexyl-4-hydroxybenzyl)isocyanurate.

1.11. Benzylphosphonates, for example dimethyl-2,5-di-tert-butyl-4-hydroxybenzylphosphonate, diethyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-5-tert-butyl-4-hydroxy-3-methylbenzylphosphonate, the calcium salt of the monoethyl ester of 3,5-di-tert-butyl-4-hydroxybenzylphosphonic acid.

1.12. Acylaminophenols, for example 4-hydroxylauranilide, 4-hydroxystearanilide, octyl N-(3,5-di-tert-butyl-4-hydroxyphenyl)carbamate.

1.13. Esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid with mono- or poly-

hydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.14. Esters of β -(5-tert-butyl-4-hydroxy-3-methylphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.15. Esters of β -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.16. Esters of 3,5-di-tert-butyl-4-hydroxyphenyl acetic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.17. Amides of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid e.g. N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hexamethylenediamine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)trimethylenediamine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazine.

1.18. Ascorbic acid (vitamin C)

1.19. Aminic antioxidants, for example N,N'-di-isopropyl-p-phenylenediamine, N,N'-di-

sec-butyl-p-phenylenediamine, N,N'-bis(1,4-dimethylpentyl)-p-phenylenediamine, N,N'-bis(1-ethyl-3-methylpentyl)-p-phenylenediamine, N,N'-bis(1-methylheptyl)-p-phenylenediamine, N,N'-dicyclohexyl-p-phenylenediamine, N,N'-diphenyl-p-phenylenediamine, N,N'-bis(2-naphthyl)-p-phenylenediamine, N-isopropyl-N'-phenyl-p-phenylenediamine, N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine, N-(1-methylheptyl)-N'-phenyl-p-phenylenediamine, N-cyclohexyl-N'-phenyl-p-phenylenediamine, 4-(p-toluenesulfamoyl)-diphenylamine, N,N'-dimethyl-N,N'-di-sec-butyl-p-phenylenediamine, diphenylamine, N-allyldiphenylamine, 4-isopropoxydiphenylamine, N-phenyl-1-naphthylamine, N-(4-tert-octylphenyl)-1-naphthylamine, N-phenyl-2-naphthylamine, octylated diphenylamine, for example p,p'-di-tert-octyldiphenylamine, 4-n-butylaminophenol, 4-butyrylamino-phenol, 4-nonanoylamino-phenol, 4-dodecanoylamino-phenol, 4-octadecanoylamino-phenol, bis(4-methoxyphenyl)amine, 2,6-di-tert-butyl-4-dimethylaminomethylphenol, 2,4'-di-aminodiphenylmethane, 4,4'-diaminodiphenylmethane, N,N,N',N'-tetramethyl-4,4'-diaminodiphenylmethane, 1,2-bis[(2-methylphenyl)amino]ethane, 1,2-bis(phenylamino)propane, (o-tolyl)biguanide, Bis[4-(1',3'-dimethylbutyl)phenyl]amine, tert-octylated N-phenyl-1-naphthylamine, a mixture of mono- and dialkylated tert-butyl/tert-octyldiphenylamines, a mixture of mono- and dialkylated nonyldiphenylamines, a mixture of mono- and dialkylated dodecyldiphenylamines, a mixture of mono- and dialkylated isopropyl/isohexyldiphenylamines, a mixture of mono- und dialkylated tert-butyldiphenylamines, 2,3-dihydro-3,3-dimethyl-4H-1,4-benzothiazine, phenothiazine, a mixture of mono- und dialkylated tert-butyl/tert-octylphenothiazines, a mixture of mono- und dialkylated tert-octylphenothiazines, N-allylphenothiazin, N,N,N',N'-tetraphenyl-1,4-diaminobut-2-ene, N,N-bis(2,2,6,6-tetramethyl-piperid-4-yl-hexamethylenediamine, bis(2,2,6,6-tetramethylpiperid-4-yl)sebacate, 2,2,6,6-tetramethylpiperidin-4-one, 2,2,6,6-tetramethylpiperidin-4-ol.

2. UV absorbers and light stabilisers

2.1. 2-(2'-Hydroxyphenyl)benzotriazoles, for example 2-(2'-hydroxy-5'-methylphenyl)-benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-5'-(1,1,3,3-tetramethylbutyl)phenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-methylphenyl)-5-chloro-benzotriazole, 2-(3'-sec-butyl-5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-4'-octyloxyphenyl)benzotriazole, 2-(3',5'-di-tert-amyl-2'-hydroxyphenyl)benzotriazole, 2-(3',5'-bis-(α,α -dimethylbenzyl)-2'-hydroxyphenyl)benzotriazole, mixture of 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxy-carbonyl)ethyl)phenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)-carbonyl]ethyl)-2'-hydroxyphenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-

methoxycarbonylethyl)phenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonylethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-5'-(2-(2-ethylhexyloxy)carbonylethyl)-2'-hydroxyphenyl)benzotriazole, 2-(3'-dodecyl-2'-hydroxy-5'-methylphenyl)benzotriazole, and 2-(3'-tert-butyl-2'-hydroxy-5'-(2-isooctyloxycarbonylethyl)phenyl)benzotriazole, 2,2'-methylene-bis[4-(1,1,3,3-tetramethylbutyl)-6-benzotriazole-2-ylphenol]; the transesterification product of 2-[3'-tert-butyl-5'-(2-methoxycarbonylethyl)-2'-hydroxyphenyl]-2H-benzotriazole with polyethylene glycol 300; $[R-CH_2CH_2-COO(CH_2)_3]_2^-$, where R = 3'-tert-butyl-4'-hydroxy-5'-2H-benzotriazol-2-ylphenyl.

2.2. 2-Hydroxybenzophenones, for example the 4-hydroxy, 4-methoxy, 4-octyloxy, 4-decyloxy, 4-dodecyloxy, 4-benzyloxy, 4,2',4'-trihydroxy and 2'-hydroxy-4,4'-dimethoxy derivatives.

2.3. Esters of substituted and unsubstituted benzoic acids, as for example 4-tertbutylphenyl salicylate, phenyl salicylate, octylphenyl salicylate, dibenzoyl resorcinol, bis(4-tert-butylbenzoyl) resorcinol, benzoyl resorcinol, 2,4-di-tertbutylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate, hexadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, octadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, 2-methyl-4,6-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate.

2.4. Acrylates, for example ethyl α -cyano- β,β -diphenylacrylate, isooctyl α -cyano- β,β -diphenylacrylate, methyl α -carbomethoxycinnamate, methyl α -cyano- β -methyl-p-methoxycinnamate, butyl α -cyano- β -methyl-p-methoxy-cinnamate, methyl α -carbomethoxy-p-methoxycinnamate and N-(β -carbomethoxy- β -cyanovinyl)-2-methylindoline.

2.5. Nickel compounds, for example nickel complexes of 2,2'-thio-bis-[4-(1,1,3,3-tetramethylbutyl)phenol], such as the 1:1 or 1:2 complex, with or without additional ligands such as n-butylamine, triethanolamine or N-cyclohexyldiethanolamine, nickel dibutyldithiocarbamate, nickel salts of the monoalkyl esters, e.g. the methyl or ethyl ester, of 4-hydroxy-3,5-di-tert-butylbenzylphosphonic acid, nickel complexes of ketoximes, e.g. of 2-hydroxy-4-methylphenyl undecylketoxime, nickel complexes of 1-phenyl-4-lauroyl-5-hydroxypyrazole, with or without additional ligands.

2.6. Sterically hindered amines, for example bis(2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(2,2,6,6-tetramethyl-4-piperidyl)succinate, bis(1,2,2,6,6-pentamethyl-4-piperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(1,2,2,6,6-pentamethyl-

4-piperidyl) n-butyl-3,5-di-tert-butyl-4-hydroxybenzylmalonate, the condensate of 1-(2-hydroxyethyl)-2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, the condensate of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-tert-octyl-amino-2,6-dichloro-1,3,5-triazine, tris(2,2,6,6-tetramethyl-4-piperidyl)nitritotriacetate, tetrakis(2,2,6,6-tetramethyl-4-piperidyl)-1,2,3,4-butane-tetracarboxylate, 1,1'-(1,2-ethane-diyl)bis(3,3,5,5-tetramethylpiperazinone), 4-benzoyl-2,2,6,6-tetramethylpiperidine, 4-stearyl-2,2,6,6-tetramethylpiperidine, bis(1,2,2,6,6-pentamethylpiperidyl)-2-n-butyl-2-(2-hydroxy-3,5-di-tert-butylbenzyl)malonate, 3-n-octyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decan-2,4-dione, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)succinate, the condensate of N,N'-bis-(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-morpholino-2,6-dichloro-1,3,5-triazine, the condensate of 2-chloro-4,6-bis(4-n-butylamino-2,2,6,6-tetramethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, the condensate of 2-chloro-4,6-di-(4-n-butylamino-1,2,2,6,6-pentamethylpiperidyl)-1,3,5-triazine and 1,2-bis-(3-aminopropylamino)ethane, 8-acetyl-3-dodecyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, 3-dodecyl-1-(2,2,6,6-tetramethyl-4-piperidyl)pyrrolidin-2,5-dione, 3-dodecyl-1-(1,2,2,6,6-pentamethyl-4-piperidyl)pyrrolidine-2,5-dione, a mixture of 4-hexadecyloxy- and 4-stearyl-2,2,6,6-tetramethylpiperidine, a condensation product of N,N'-bis-(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-cyclohexylamino-2,6-dichloro-1,3,5-triazine, a condensation product of 1,2-bis(3-aminopropylamino)ethane and 2,4,6-trichloro-1,3,5-triazine as well as 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS Reg. No. [136504-96-6]); N-(2,2,6,6-tetramethyl-4-piperidyl)-n-dodecylsuccinimid, N-(1,2,2,6,6-pentamethyl-4-piperidyl)-n-dodecylsuccinimid, 2-undecyl-7,7,9,9-tetramethyl-1-oxa-3,8-diaza-4-oxo-spiro[4.5]decane, a reaction product of 7,7,9,9-tetramethyl-2-cyclo-undecyl-1-oxa-3,8-diaza-4-oxospiro [4.5]decane und epichlorohydrin.

2.7. Oxamides, for example 4,4'-dioctyloxyoxanilide, 2,2'-diethoxyoxanilide, 2,2'-dioctyloxy-5,5'-di-tert-butoxanilide, 2,2'-didodecyloxy-5,5'-di-tert-butoxanilide, 2-ethoxy-2'-ethyloxanilide, N,N'-bis(3-dimethylaminopropyl)oxamide, 2-ethoxy-5-tert-butyl-2'-ethoxanilide and its mixture with 2-ethoxy-2'-ethyl-5,4'-di-tert-butoxanilide and mixtures of ortho- and para-methoxy-disubstituted oxanilides and mixtures of o- and p-ethoxy-disubstituted oxanilides.

2.8. 2-(2-Hydroxyphenyl)-1,3,5-triazines, for example 2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2,4-bis(2-hydroxy-4-propyloxyphenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-

4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-tridecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-butyloxy-propoxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-octyloxy-propyloxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[4-(dodecyloxy/tridecyloxy-2-hydroxypropoxy)-2-hydroxy-phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-dodecyloxy-propoxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-hexyloxy)phenyl-4,6-diphenyl-1,3,5-triazine, 2-(2-hydroxy-4-methoxyphenyl)-4,6-diphenyl-1,3,5-triazine, 2,4,6-tris[2-hydroxy-4-(3-butoxy-2-hydroxy-propoxy)phenyl]-1,3,5-triazine, 2-(2-hydroxyphenyl)-4-(4-methoxyphenyl)-6-phenyl-1,3,5-triazine.

3. Metal deactivators, for example N,N'-diphenyloxamide, N-salicylal-N'-salicyloyl hydrazine, N,N'-bis(salicyloyl) hydrazine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenyl-propionyl) hydrazine, 3-salicyloylamino-1,2,4-triazole, bis(benzylidene)oxalyl dihydrazide, oxanilide, isophthaloyl dihydrazide, sebacoyl bisphenylhydrazide, N,N'-diacetyladipoyl dihydrazide, N,N'-bis(salicyloyl)oxalyl dihydrazide, N,N'-bis(salicyloyl)-thiopropionyl dihydrazide.

4. Phosphites and phosphonites, for example triphenyl phosphite, diphenyl alkyl phosphites, phenyl dialkyl phosphites, tris(nonylphenyl) phosphite, trilauryl phosphite, trioctadecyl phosphite, distearyl pentaerythritol diphosphite, tris(2,4-di-tert-butylphenyl) phosphite, diisodecyl pentaerythritol diphosphite, bis(2,4-di-tert-butylphenyl) pentaerythritol diphosphite, bis(2,6-di-tert-butyl-4-methylphenyl)-pentaerythritol diphosphite, diisodecyl-oxy-pentaerythritol diphosphite, bis(2,4-di-tert-butyl-6-methylphenyl)pentaerythritol diphosphite, bis(2,4,6-tris(tert-butylphenyl)pentaerythritol diphosphite, tristearyl sorbitol triphosphite, tetrakis(2,4-di-tert-butylphenyl) 4,4'-biphenylene diphosponite, 6-isooctyloxy-2,4,8,10-tetra-tert-butyl-12H-dibenz[d,g]-1,3,2-dioxaphosphocin, 6-fluoro-2,4,8,10-tetra-tert-butyl-12-methyl-dibenz[d,g]-1,3,2-dioxaphosphocin, bis(2,4-di-tert-butyl-6-methylphenyl)methylphosphite, bis(2,4-di-tert-butyl-6-methylphenyl)ethylphosphite.

5. Hydroxylamines, for example, N,N-dibenzylhydroxylamine, N,N-diethylhydroxylamine, N,N-dioctylhydroxylamine, N,N-dilaurylhydroxylamine, N,N-ditetradecylhydroxylamine, N,N-dihexadecylhydroxylamine, N,N-dioctadecylhydroxylamine, N-hexadecyl-N-octadecylhydroxylamine, N-heptadecyl-N-octadecylhydroxylamine, N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

6. Nitrones, for example, N-benzyl-alpha-phenyl-nitron, N-ethyl-alpha-methyl-nitron, N-octyl-alpha-heptyl-nitron, N-lauryl-alpha-undecyl-nitron, N-tetradecyl-alpha-tridecyl-nitron, N-hexadecyl-alpha-pentadecyl-nitron, N-octadecyl-alpha-heptadecyl-nitron, N-hexadecyl-alpha-heptadecyl-nitron, N-octadecyl-alpha-pentadecyl-nitron, N-heptadecyl-alpha-heptadecyl-nitron, N-octadecyl-alpha-hexadecyl-nitron, nitron derived from N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

7. Thiosynergists, for example, dilauryl thiodipropionate or distearyl thiodipropionate.

8. Peroxide scavengers, for example esters of β -thiodipropionic acid, for example the lauryl, stearyl, myristyl or tridecyl esters, mercaptobenzimidazole or the zinc salt of 2-mercaptobenzimidazole, zinc dibutyldithiocarbamate, dioctadecyl disulfide, pentaerythritol tetrakis(β -dodecylmercapto)propionate.

9. Polyamide stabilisers, for example, copper salts in combination with iodides and/or phosphorus compounds and salts of divalent manganese.

10. Basic co-stabilisers, for example, melamine, polyvinylpyrrolidone, dicyandiamide, triallyl cyanurate, urea derivatives, hydrazine derivatives, amines, polyamides, polyurethanes, alkali metal salts and alkaline earth metal salts of higher fatty acids for example calcium stearate, zinc stearate, magnesium behenate, magnesium stearate, sodium ricinoleate and potassium palmitate, antimony pyrocatecholate or tin pyrocatecholate.

11. Nucleating agents, for example, inorganic substances such as talcum, metal oxides such as titanium dioxide or magnesium oxide, phosphates, carbonates or sulfates of, preferably, alkaline earth metals; organic compounds such as mono- or polycarboxylic acids and the salts thereof, e.g. 4-tert-butylbenzoic acid, adipic acid, diphenylacetic acid, sodium succinate or sodium benzoate; polymeric compounds such as ionic copolymers ("ionomers").

12. Fillers and reinforcing agents, for example, calcium carbonate, silicates, glass fibres, glass bulbs, asbestos, talc, kaolin, mica, barium sulfate, metal oxides and hydroxides, carbon black, graphite, wood flour and flours or fibers of other natural products, synthetic fibers.

13. Other additives, for example, plasticisers, lubricants, emulsifiers, pigments, rheology additives, catalysts, flow-control agents, optical brighteners, flameproofing agents, antista-

tic agents and blowing agents.

14. Benzofuranones and indolinones, for example those disclosed in US-A-4 325 863, US-A-4 338 244, US-A-5 175 312, US-A-5 216 052, US-A-5 252 643, DE-A-4 316 611, DE-A-4 316 622, DE-A-4 316 876, EP-A-0 589 839 or EP-A-0 591 102 or 3-[4-(2-acetoxyethoxy)phenyl]-5,7-di-tert-butyl-benzofuran-2-one, 5,7-di-tert-butyl-3-[4-(2-stearoyloxyethoxy)phenyl]benzofuran-2-one, 3,3'-bis[5,7-di-tert-butyl-3-(4-[2-hydroxyethoxy]phenyl)benzofuran-2-one], 5,7-di-tert-butyl-3-(4-ethoxyphenyl)benzofuran-2-one, 3-(4-acetoxy-3,5-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(3,5-dimethyl-4-pivaloyloxyphenyl)-5,7-di-tert-butyl-benzofuran-2-one.

The weight ratio between the novel stabilizer mixture and the conventional additives can be, for example, from 1:0.5 to 1:5.


The invention furthermore relates to the use of the novel stabilizer mixture for stabilizing organic material against oxidative, thermal or light-induced degradation.

The organic materials stabilized by means of the novel stabilizer system are distinguished not only by significantly improved light stability, but also in some cases by improved thermal stability.

The example below illustrates the invention in greater detail. All percentages are by weight, unless stated otherwise.


Light stabilizers used in Examples 1-2:

Compound A:




The mean value of n_1 is 5.8.

Compound B-1:



The mean value of n_2 is 4.5.


Compound B-2:




The mean value of n_2 is 3.5.

Compound C:


A product obtainable by reacting a product, obtained by reaction of a polyamine of the formula



with cyanuric chloride, with a compound of the formula




Compound D:



The mean value of n_4 is 5.1.


Compound E:

A mixture of the compounds




(VIa),

and




in which the mean value of n_5 is about 3.9 and the mean value of n_5^* is about 4.2, and the ratio between (VIa) and (VIb) is about 4:1.

Compound F-1:




The mean value of n_6 is 3.2.

Compound F-2:




Compound G-1:



The mean value of n_7 is 2.5.

Compound G-2:



The mean value of n_7 is 2.5.

Example 1: Light stabilization action in polypropylene block copolymer films.

100 parts of polypropylene block copolymer powder are homogenized for 10 minutes at 200°C in a Brabender plastograph with 0.05 part of pentaerythrityl tetrakis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate, 0.10 part of tris(2,4-di-tert-butylphenyl) phosphite, 0.1 part of calcium stearate and the light stabilizers shown in Table 1. The composition obtained is removed from the compounder as rapidly as possible and pressed in a toggle press to give a sheet with a thickness of 2-3 mm. A piece of the resultant green pressing is cut out and pressed between two high-gloss hard aluminium foils for 6 minutes at 260°C by means of a hydraulic bench press to give a sheet with a thickness of 0.5 mm, which is immediately cooled in a water-cooled press. Pieces each measuring 60 mm × 25 mm are then stamped out of this 0.5 mm sheet and exposed to light in a WEATHER-O-METER Ci 65 (black panel temperature 63±2°C, no exposure to rain water). These test specimens are removed from the exposure apparatus at regular intervals and tested for their carbonyl content in an IR spectrometer. The increase in the carbonyl absorbance during exposure is a measure of the photooxidative degradation of the polymer and is known from experience to be associated with a deterioration in the mechanical properties. The results are shown in Table 1.

Table 1:

<u>Light stabilizer</u>	<u>Hours in WEATHER-O-METER Ci 65 to 0.2 carbonyl absorbance</u>
None	110
0.2 % of compound A	2560
0.2 % of compound B-1	1740
0.2 % of compound B-2	2280
0.2 % of compound C	2400
0.2 % of compound D	2040

0.2 % of compound E	1710
0.2 % of compound F-1	505
0.2 % of compound F-2	260
0.2 % of compound G-1	1410
0.2 % of compound G-2	1230
0.1 % of compound A and 0.1 % of compound B-1	2890
0.1 % of compound A and 0.1 % of compound B-2	2880
0.1 % of compound A and 0.1 % of compound C	2990
0.1 % of compound A and 0.1 % of compound D	2950
0.1 % of compound A and 0.1 % of compound E	2400
0.1 % of compound A and 0.1 % of compound F-1	1840
0.1 % of compound A and 0.1 % of compound F-2	1610
0.1 % of compound A and 0.1 % of compound G-1	2160
0.1 % of compound A and 0.1 % of compound G-2	2100

Example 2: Light stabilization action in high-density polyethylene films.

100 parts of high-density polyethylene powder (density = 0.965 g/cm^3) are homogenized for 10 minutes at 180°C in a Brabender plastograph with 0.033 part of pentaerythrityl tetrakis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate], 0.066 part of tris(2,4-di-tert-butylphenyl) phosphite, 0.1 part of calcium stearate and the light stabilizers shown in Table 2. The composition obtained is removed from the compounder as rapidly as possible and pressed in a toggle press to give a sheet with a thickness of 2-3 mm. A piece of the resultant green pressing is cut out and pressed between two high-gloss hard aluminium foils for 6 minutes at 210°C by means of a hydraulic bench press to give a sheet with a thickness of 0.5 mm, which is immediately cooled in a water-cooled press. Pieces measuring $60 \text{ mm} \times 25 \text{ mm}$ are then stamped out of this 0.5 mm sheet and exposed to light in a Weather-O-Meter Ci 65 (black panel temperature $63 \pm 2^\circ\text{C}$, no exposure to rain water). These test specimens are removed from the exposure apparatus at regular intervals and tested for their vinyl group content in an IR spectrometer. The increase in the vinyl absorbance (909 cm^{-1}) during exposure is a measure of the photooxidative degradation of the polymer and is known from experience to be associated with a deterioration in the mechanical properties. The results are shown in Table 2.

Table 2:


<u>Light stabilizer</u>	<u>Vinyl absorbance after 7222 hours in the WEATHER-O-METER Ci 65</u>
None	0.097 after 318 hours
0.1 % of compound A	0.039
0.1 % of compound B-1	0.052
0.1 % of compound B-2	0.043
0.1 % of compound C	0.054
0.1 % of compound D	0.039
0.1 % of compound E	0.046

0.1 % of compound F-1	0.058
0.1 % of compound F-2	0.143 after 5286 hours
0.1 % of compound G-1	0.040
0.1 % of compound G-2	0.040
0.05 % of compound A and 0.05 % of compound B-1	0.038
0.05 % of compound A and 0.05 % of compound B-2	0.038
0.05 % of compound A and 0.05 % of compound C	0.040
0.05 % of compound A and 0.05 % of compound D	0.029
0.05 % of compound A and 0.05 % of compound E	0.039
0.05 % of compound A and 0.05 % of compound F-1	0.036
0.05 % of compound A and 0.05 % of compound F-2	0.045
0.05 % of compound A and 0.05 % of compound G-1	0.030
0.05 % of compound A and 0.05 % of compound G-2	0.035

WHAT IS CLAIMED IS:

1. A stabilizer mixture comprising a component a) and a component b), c), d), e), f) or g), where

component a) is at least one compound of the formula I




in which R₁ is C₁-C₁₀alkyl, C₅-C₁₂cycloalkyl, C₁-C₄alkyl-substituted C₅-C₁₂cycloalkyl, phenyl or C₁-C₁₀alkyl-substituted phenyl,

R₂ is C₃-C₁₀alkylene,

R₃ is hydrogen, C₁-C₈alkyl, O[•], -CH₂CN, C₃-C₆alkenyl, C₇-C₉phenylalkyl, C₇-C₉phenylalkyl which is substituted on the phenyl radical by C₁-C₄alkyl; or C₁-C₈acyl and,

n₁ is a number from 1 to 50;

component b) is at least one compound of the formula (II)



in which R₄, R₆, R₇ and R₈, independently of one another, are hydrogen, C₁-C₁₂alkyl, C₅-C₁₂cycloalkyl, C₁-C₄alkyl-substituted C₅-C₁₂cycloalkyl, phenyl, phenyl which is substituted by -OH and/or C₁-C₁₀alkyl; C₇-C₉phenylalkyl, C₇-C₉phenylalkyl which is

substituted on the phenyl radical by -OH and/or C₁-C₁₀alkyl; or a group of the formula III



R₅ is C₂-C₁₈alkylene, C₅-C₇cycloalkylene or C₁-C₄alkylenedi(C₅-C₇cycloalkylene), or the radicals R₄, R₅ and R₆, together with the nitrogen atoms to which they are bonded, perform a 5- to 10-membered heterocyclic ring, or


R₇ and R₈, together with the nitrogen atom to which they are bonded, form a 5- to 10-membered heterocyclic ring,

R₉ is as defined for R₃,

n₂ is a number from 2 to 50, and

at least one of the radicals R₄, R₆, R₇ and R₈ is a group of the formula (III);

component c) is a product obtainable by reacting a product, obtained by reaction of a polyamine of the formula IVa with cyanuric chloride, with a compound of the formula IVb




in which n₃', n₃'' and n₃''', independently of one another are a number from 2 to 12,

R₁₀ is hydrogen, C₁-C₁₂alkyl, C₅-C₁₂cycloalkyl, phenyl or C₇-C₉phenylalkyl, and



R₁₁ is as defined for R₃;

component d) is at least one compound of the formula (V)




in which R_{12} is hydrogen or methyl,
 R_{13} is a direct bond or C_1 - C_{10} alkylene and
 n_4 is a number from 2 to 50;

component e) is at least one compound of the formulae (VIa) and (VIb)



in which n_5 and n_5^* independently of one another are a number from 2 to 50;

component f) is at least one compound of the formula (VII)



(VII)

in which R₁₄ and R₁₈, independently of one another, are a direct bond or an -N(X₁)-CO-X₂-CO-N(X₃)- group, where X₁ and X₃, independently of one another, are hydrogen, C₁-C₈alkyl, C₅-C₁₂cycloalkyl, phenyl, C₇-C₉phenylalkyl or a group of the formula III,

X₂ is a direct bond or C₁-C₄alkylene,


R₁₅ is as defined for R₃,

R₁₆, R₁₇, R₂₀ and R₂₁, independently of one another, are hydrogen, C₁-C₃₀alkyl, C₅-C₁₂cycloalkyl or phenyl,

R₁₉ is hydrogen, C₁-C₃₀alkyl, C₅-C₁₂cycloalkyl, C₇-C₉phenylalkyl, phenyl or a group of the formula III, and

n₆ is a number from 1 to 50;

component g) is at least one compound of the formula (VIII)



(VIII)

in which R_{22} , R_{23} , R_{24} , R_{25} and R_{26} , independently of one another, are a direct bond or C_1 - C_{10} alkylene,

R_{27} is as defined for R_3 , and

n_7 is a number from 1 to 50.

2. A stabilizer mixture according to claim 1, in which R_3 , R_9 , R_{11} , R_{15} and R_{27} are hydrogen or methyl.

3. A stabilizer mixture according to claim 1, in which

R_1 is C_1 - C_4 alkyl, C_5 - C_8 cycloalkyl or phenyl,

R_2 is C_3 - C_6 alkylene, and

n_1 is a number from 1 to 25;

R_4 , R_6 , R_7 and R_8 , independently of one another, are hydrogen, C_1 - C_8 alkyl, C_5 - C_8 cycloalkyl, phenyl, C_7 - C_9 phenylalkyl or a group of the formula III, or the radicals R_7 and R_8 , together with the nitrogen atom to which they are bonded, form a 6-membered heterocyclic ring,

R_5 is C_2 - C_{10} alkylene, and

n_2 is a number from 2 to 25;

n_3' , n_3'' and n_3''' , independently of one another, are a number from 2 to 4, and

R_{10} is C_1 - C_4 alkyl;

R_{12} is hydrogen,

R_{13} is ethylene, and

n_4 is a number from 2 to 25;

n_5 and n_5^* , independently of one another, are a number from 2 to 25;

R_{14} and R_{18} are a direct bond or an $-N(X_1)-CO-X_2-CO-N(X_3)-$ group, X_1 and X_3 , independently of one another, are hydrogen or C_1 - C_4 alkyl,

X_2 is a direct bond,

R_{16} and R_{20} are C_1 - C_{25} alkyl or phenyl,

R_{17} and R_{21} are hydrogen or C_1 - C_4 alkyl,

R_{19} is C_1 - C_{25} alkyl or a group of the formula III, and


n_6 is a number from 1 to 25;

R_{22} , R_{24} , R_{25} and R_{26} are C_1 - C_4 alkylene,

R_{23} is a direct bond, and



n_7 is a number from 1 to 25.


4. A stabilizer mixture according to claim 1, in which component a) is at least one compound of the formula I-A



in which n_1 is a number from 1 to 20;

component b) is at least one compound of the formula (II-B-1), (II-B-2) or (II-B-3)






in which n_2 is a number from 2 to 20;


component c) is a product obtainable by reacting a product, obtained by reaction of a polyamine of the formula



with cyanuric chloride, with a compound of the formula






component d) is at least one compound of the formula (V-D)



in which n_4 is a number from 2 to 20;


n_5 and n_5^* in component e) are, independently of one another, a number from 2 to 20;

component f) is at least one compound of the formula (VII-F-1), (VII-F-2) or (VII-F-3)



in which n_6 is a number from 1 to 20;

component g) is at least one compound of the formula (VIII-G)



(VIII-G)


in which R_{27} is hydrogen or methyl, and n_7 is a number from 1 to 20.

5. A stabilizer mixture according to claim 1, which comprises components a) and b).
6. A stabilizer mixture according to claim 1, which comprises components a) and c).
7. A stabilizer mixture according to claim 1, which comprises components a) and d).
8. A stabilizer mixture according to claim 1, which comprises components a) and e).
9. A stabilizer mixture according to claim 1, which comprises components a) and f).
10. A stabilizer mixture according to claim 1, which comprises components a) and g).
11. A composition comprising an organic material which is sensitive to oxidative, thermal or light-induced degradation and a stabilizer mixture according to claim 1.
12. A composition according to claim 11, in which the organic material is a polyolefin.
13. A composition according to claim 11, in which the organic material is polyethylene, polypropylene or a copolymer of polyethylene or polypropylene.
14. A method for stabilizing an organic material which is sensitive to oxidative, thermal or light-induced degradation, which comprises incorporating in said organic material a stabilizer mixture according to claim 1.

Fetherstonhaugh & Co.,
Ottawa, Canada
Patent Agents

Synergistic stabilizer mixtureAbstract of the disclosure

A synergistic stabilizer mixture comprising a component a) and, for example, a component b), where component a) is at least one compound of the formula I



in which R_1 is C_1 - C_{10} alkyl, C_5 - C_{12} cycloalkyl, C_1 - C_4 alkyl-substituted C_5 - C_{12} cycloalkyl, phenyl or C_1 - C_{10} alkyl-substituted phenyl,

R_2 is C_3 - C_{10} alkylene,


R_3 is hydrogen, C_1 - C_8 alkyl, O^- , $-CH_2CN$, C_3 - C_6 alkenyl, C_7 - C_9 phenylalkyl,

C_7 - C_9 phenylalkyl which is substituted on the phenyl radical by C_1 - C_4 alkyl; or C_1 - C_8 acyl,

and

n_1 is a number from 1 to 50,

and component b) is, for example, a compound of the formula



in which n_2 is a number from 2 to 20.